

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) Publication number:

**0 217 252 B1**

(12)

## EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: 13.11.91 (51) Int. Cl.<sup>5</sup>: **B65D 65/40, B32B 27/32**

(21) Application number: **86113010.2**

(22) Date of filing: **20.09.86**

(54) **Thermoplastic multi-layer packaging film and bags made therefrom.**

(30) Priority: 30.09.85 IT 2230585  
16.05.86 IT 2045786

(43) Date of publication of application:  
08.04.87 Bulletin 87/15

(45) Publication of the grant of the patent:  
13.11.91 Bulletin 91/46

(84) Designated Contracting States:  
**AT BE CH DE FR GB IT LI LU NL SE**

(56) References cited:  
**DE-A- 3 401 218 GB-A- 1 295 656**  
**GB-A- 1 557 920 JP-A- 75 258**  
**US-A- 3 549 389 US-A- 4 182 457**  
**US-A- 4 198 256 US-A- 4,380 567**  
**US-A- 4 424 243**

(73) Proprietor: **W.R. Grace & Co.-Conn. (a Connecticut corp.)**  
**Grace Plaza 1114 Avenue of the Americas**  
**New York New York 10036(US)**

(72) Inventor: **Williams, Richard Stephen**  
**Via XXV April, 2**  
**Taino (Varese)(IT)**  
Inventor: **Quacquarella, Cesare**  
**Via Misurata, 7**  
**Milano(IT)**

(74) Representative: **UEXKÜLL & STOLBERG Patentanwälte**  
**Beselerstrasse 4**  
**W-2000 Hamburg 52(DE)**

**EP 0 217 252 B1**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

## Description

The invention relates to thermoplastic multi-layer packaging films and bags or pouches made therefrom. In particular this invention relates to films and bags having superior heat shrink and cold seal properties, which give good seal strength even through contamination like grease or blood, and which allow the application of higher shrink temperatures due to their improved seal strength at elevated temperatures.

Shrinkable and heat sealable thermoplastic films are being used in packaging of non-food and food products like meat, cheese, poultry and the like. Many attempts have been made to combine good shrink properties with satisfactory sealability and good seal strength both at room temperature and at higher temperatures but there is still room for improvement.

A laminate film known from U.S.-A-3 ,741 ,253 comprises a core layer of a vinylidene chloride copolymer between a layer of a cross-linked ethylene-vinyl acetate copolymer used as a sealant and an outer layer of ethylene-vinylacetate copolymer which is not crosslinked. The ethylene-vinylacetate copolymer has improved properties over the previously used polyethylene, especially when it has been cross-linked by irradiation.

As disclosed in U.S.-A- 4 064 296 the core layer may also consist of a hydrolyzed ethylene-vinyl acetate copolymer. It has similar oxygen barrier properties as vinylidene chloride copolymers and offers the advantage that it may be irradiated without discoloration.

Certain advantages have been achieved by using an ionomeric resin as sealing layer. They result in a higher seal strength at elevated temperatures thus allowing higher shrink temperatures. However, their cold seal strength is not fully satisfactory. This latter property is important in modern automated bag packaging processes in which the seals are subjected to substantial stress when the bags are opened and loaded with the article to be packed.

More recently low density linear polyethylenes have become commercially available and have also been proposed for packaging applications. Actually the so called linear low density polyethylenes are copolymers of ethylene and varying amounts of higher  $\alpha$ -olefins with e.g. 5 to 10 carbon atoms per molecule (U.S. -A- 4 ,076 ,698) or 3 to 8 carbon atoms per molecule (EP-A-120503). Depending on their density these materials are referred to as linear low density polyethylene (LLDPE) or very low density polyethylene (VLDPE), the separation line being at a density of about 0.910 g/cm<sup>3</sup>. Some properties of VLDPE have been described in *Plastics Technology*, September 1984, page 113 and October 1984, page 13 as well as in a company brochure published in February 1984 by DSM in the Netherlands and entitled "Stamilex PE". Their properties are said to be a unique combination between those of standard polyethylene and polyolefinic rubbers. Their sealability and their compatibility with other polymers have been mentioned.

US patent 4 424 243 discloses a heat-shrinkable laminate film which has outer surface layers of linear low density polyethylene (LLDPE) polymers which definition includes ethylene/ $\alpha$ -olefin copolymers. The  $\alpha$ -olefin may be butene(1), pentene(1), 4-methyl pentene(1), hexene(1) and octene(1). The comonomer content may be between 1.0 and 30% and the density between 0.900 and 0.950, especially 0.900 and 0.940 g/cm<sup>3</sup>. Four copolymers have been selected for the examples which have a density between 0.922 and 0.935 g/cm<sup>3</sup> and the comonomer content of which is not specified. The sealing properties of said surface layers have not been tested and are not mentioned.

The disclosure of JA-A-82 752/58 is quite similar as far as the definition of the ethylene copolymers is concerned. The copolymers used in the examples have a density of 0.922 g/cm<sup>3</sup>, the comonomer content is not specified. In this case it is further important to note that in all examples a mixture of an ethylene copolymer and EVA has been used for the seal layer A.

US patent 4 380 567 discloses a film structure which comprises a core layer of high density polyethylene and outer surface layers of an ethylene/C<sub>5</sub>- to C<sub>10</sub>  $\alpha$ -olefin having a density of 0.910 to 0.940 g/cm<sup>3</sup>. The ethylene content of these copolymers is between 90 and 99.5 mol%. The examples use an ethylene/4-methyl-pentene(1) copolymer having a density of 0.922 g/cm<sup>3</sup>, 0.935 g/cm<sup>3</sup> and 0.916 g/cm<sup>3</sup>. The comonomer content is not specified, it may be between 1.5 and 25 wt.% (= 0.5 to 10 mol%).

It is an object of the present invention to provide a multi-layer laminated packaging film and bags made therefrom which have improved shrink characteristics over the materials used in the past. This means that at a given temperature the shrink in percent (the mean between the shrink in the longitudinal and transversal direction) should be higher and the tolerated maximum shrink temperature should also be higher. The maximum shrink temperature is dependent on the seal strength at elevated temperatures.

It is a further object of this invention to provide a packaging material with improved cold seal strength and thereby a reduced risk of breakages when bags made of the film material are utilized in automated loading processes.

It is yet another object of the present invention to provide a packaging material which gives reliable seals even when contaminated. Especially in the packaging of meat it frequently occurs that the sealing areas are contaminated with grease or blood, both of which tend to impair the sealing between hitherto used sealing layers.

5 Finally and most importantly it is an object of this invention to provide a material combining the above advantages, i.e. improved shrinkability, increased maximum shrink temperature, good cold seal strength and sealability through contamination.

It has been found that the above-mentioned objects are achieved by the present invention which is directed to a thermoplastic multi-layer packaging film comprising at least an outer polymer layer, an inner  
10 heat sealing layer and optionally an oxygen barrier layer between said inner and said outer layer, and which is characterized in that the heat sealing layer comprises a linear copolymer of ethylene and x to y% by weight, based on the copolymer, of an  $\alpha$ -olefin with 4 to 8 carbon atoms, whereby  $x = 0.5n_C + 8$  and  $y = 1.25 n_C + 15$  with  $n_C$  being the number of carbon atoms in the  $\alpha$ -olefin, said copolymer having a density of 0.915 g/cm<sup>3</sup> or less.

15 Preferably the heat sealing layer comprises a copolymer of ethylene and 12 to 20% by weight, based on the copolymer, of an  $\alpha$ -olefin with 4 to 8 carbon atoms.

It has surprisingly been found that both the heat shrink properties and the cold seal strength of the laminated packaging film depend on the comonomer content of the ethylene copolymer used as the sealing layer. In order to achieve optimal results the comonomer content must increase when going from the C<sub>4</sub> -  
20  $\alpha$ -olefin (butene(1)) to the C<sub>8</sub>- $\alpha$ -olefin (octene(1)). It is particularly surprising that the films of the present invention exhibit improved shrink properties both in irradiated (cross-linked) and non-irradiated condition and that these properties as well as the seal strength are a function of the comonomer content of the linear low and very low density "polyethylene".

When using a copolymer of ethylene and butene(1) the comonomer content should be between 10 and  
25 20% by weight, based on the copolymer. Such copolymers have a density of less than 915 kg/m<sup>3</sup>. When employing a copolymer of ethylene and octene(1) the comonomer content should preferably be increased to between 12 and 25% by weight, based on the copolymer. Such copolymers have a density of 0.915 g/cm<sup>3</sup> or less.

According to the invention it is also possible to blend the ethylene/  $\alpha$ -olefin copolymer with up to 50%  
30 by weight, based on the sealing layer composition, of a polymer which is compatible with said ethylene /  $\alpha$  -olefin copolymer. Such further polymer may preferably be selected from the group comprising linear low density polyethylene (LLDPE) with a density above 920 kg/m<sup>3</sup>, linear high density polyethylene (LHDPE), low density polyethylene (LDPE), ethylene vinyl acetate (EVA), acid modified EVA, polypropylene, ethylene/propylene copolymers, ionomeric polymers and ethylene/alkylacrylate copolymers wherein the  
35 alkyl moiety has 1 to 8 C atoms, in particular ethylene-methylacrylate (EMA), ethylene-ethylacrylate (EEA) and ethylene-butylacrylate (EBA).

The ethylene/alkylacrylate copolymer which can be blended with the ethylene /  $\alpha$ -olefin in the heat sealing layer can comprise 3 to 30% by weight of alkylacrylate.

According to one embodiment of the invention the ethylene copolymer forming the sealing layer may  
40 be cross-linked by irradiation in order to improve its shrink characteristics and mechanical properties. However, such cross-linking is not necessary since a very satisfactory packaging film is also obtained without irradiation. If polyvinylidene chloride is used as core layer providing an oxygen barrier the irradiation should take place prior to the lamination of the core layer to the sealing layer since PVDC may suffer when exposed to high energy irradiation. The entire multi-layer film may be irradiated if the PVDC core layer is  
45 substituted by a core layer of partly hydrolyzed ethylene vinyl-acetate copolymer (EVOH). PVDC and EVOH are the preferred core layers since they show outstanding oxygen barrier properties.

The films are normally oriented in longitudinal and transversal direction to obtain the desired shrink properties. If a tubular film is produced by extrusion the orientation may be effected using the known air bubble method and further stretching the film by pulling. Alternatively, orientation may be achieved by deep  
50 drawing of a planar film.

The outer layer of the multi-layer packaging film of the invention may be of the same ethylene copolymer as the sealing layer, i.e. an ethylene/  $\alpha$ -olefin copolymer comprising 10 to 25% by weight, based on the copolymer, of an  $\alpha$ -olefin with 4 to 8 carbon atoms, said copolymer having a density of 0.915 g/cm<sup>3</sup> or less, or it may be selected from ethylene vinyl acetate, polyamides, and ionomeric resins. It may  
55 frequently be of advantage if an adhesive layer and/or an adhesion promoting layer is interposed between said other layers.

If bags are made from the film material the film will normally be folded so that the fold forms the bottom of the bag whereafter both sides are sealed so that the side seals close both sides of the bag. Alternatively

a bag may be formed from a tubular film in that the bottom of the bag is formed by a transverse seal across the flattened tube and the mouth is formed by severing the tube at a pre-selected distance from said transverse seal. Pouches can be obtained by sealing two film sheets at three edges.

5 The invention will be further illustrated by reference to the following examples without being limited thereto.

The following test methods were used to investigate the properties of the packaging films and to compare them with other materials.

#### 10 A. VARIABLE PRESSURE HOT BURST TEST (VPHB)

This is a test to determine the seal quality of shrinkable materials at different temperatures. The approach with this test is to immerse total seal areas into hot water and after a predetermined dwell time, the pressure inside the bag is increased at a constant rate of approx. 25.4 mm of water per second until the seal fails.

15 The mm of water pressure, at the level at which the seal fails, are recorded, and there are minimum specifications expressed in mm for each bag width. The highest is the number, the better is the seal quality at that temperature.

#### 20 B. PERCENT SHRINK

The percent shrink is measured immersing for a couple of seconds in hot water a specimen and measuring the percent of retraction, both in the longitudinal and transversal direction. The highest is the percent of shrink, the better is the performance of the material in terms of package presentation.

25 In practice, the maximum achievable percent of shrink is that measured at the temperature at which the material meets the minimum VPHB requirements expressed in mm of water pressure (see point A). To predict the shrink behaviour it is therefore useful to plot in the same diagram the % of shrink and the VPHB as a function of the temperature.

#### 30 C. COLD SEAL STRENGTH

The cold seal strength represents the seal quality at room temperature and predicts the seal performance when the bag is loaded with a product, either manually or by means of automatic loaders, which operate with a pusher, which pushes the product into the bag. The cold seal strength is measured with a modified pusher of a commercial loader, equipped with a system to record the pressure necessary to 35 open the bottom seal. The head of the pusher operates on a 6 cm length of seal and the cold seal strength is expressed in kg/6 cm. The maximum pressure recordable with this systems is 40 kg/6 cm.

The reported results are the average of 10 measurements.

The following raw materials were used in the examples :

40

45

50

55

RAW MATERIALS	ABBREVIATION	COMPOSITION	MELTING POINT	DENSITY (g/cm <sup>3</sup> )
5	E/ 15% B	ethylene-butene copolym., 15% butene	118°C	0.906
10	E/ 8% B	ethylene-butene copolym., 8% butene	121.5°C	0.918
15	E/ 6% VA	ethylene-vinylacetate copolym., 6% VA	105°C	0.926
20	E/ 9% VA	ethylene-vinylacetate cop., 9% VA	96°C	0.929
25	E/ 14% VA	ethylene-vinylacetate copolym., 14% VA	90°C	0.932
30	E/ 18% VA	ethylene-vinylacetate cop. 18% VA	91°C	0.940
35	lonomer (Na)	lonomeric resin (Na salt)	90-92°C	0.940
40	E/ 19% O	ethylene-octene copolym., 19% octene	124°C	0.911
45	E/ 13% O	ethylene-octene copolym., 13% octene	124°C	0.915
	E/ 10.5% O	ethylene-octene copolym., 10.5% octene	123°C	0.920
	Acid modifi. EVA	acid modified Ethylene-Vinylacetate	(55°C)	0.948
	PA	Polyamide (Nylon 6,12 copolymer)	140-147°C	1.06
	EVA (20% MA)	ethylene-methylacrylate copolym., 20% MA	85-90°C	0.942
	EBA (7% BA)	ethylene-butylacrylate copolym., 7% BA	98-108°C	0.923
	P/4.5% E	propylene-ethylene copolym., 4.5% E	135°C	0.900

## COMPARATIVE EXAMPLES 1 TO 4 AND EXAMPLES 1 TO 3

Multi-layer packaging films of the composition summarized below in table I were prepared in the following manner. The first two layers A and B were coextruded through a conventional tubular extruder to form a tube. After leaving the die the substrate was cooled and flattened. It was then sent through an irradiation vault where it was irradiated by high energy electrons to a dosage of about 4.5 MR. Depending on the characteristics desired this dosage could vary from 2 to 20 MR. After leaving the irradiation vault the substrate was again inflated and sent through a first tubular extrusion coating die where it received a coating of vinylidene chloride copolymer. Thereafter the still inflated and now triple-walled film passed through a second tubular extrusion coating die where it received a layer of ethylene-vinyl acetate

copolymer. After the final coating the film was cooled, collapsed and rolled-up. This tape was subsequently unrolled, fed through a bath of hot water, held at a temperature of about 80 to 98° C, and as it left the water it was inflated and blown into thin tubing with a total wall thickness of about 59 microns. This so-called "trapped bubble" technique is well known in the art. The film was then rapidly cooled to set the orientation and then rolled up for further processing.

The polyvinylidene chloride and the ethylene-vinylacetate copolymer can alternatively be coated onto the substrate using a two-ply coextrusion die.

The test results are summarized in the following table II.

Table I

Example No.	A sealing layer $\mu\text{m}$	B core layer $\mu\text{m}$	D barrier layer $\mu\text{m}$	F outer layer $\mu\text{m}$
Comp. 1	E/ 9% VA 37	-	PVDC 8	E/ 9% VA 14
Comp. 2	Ionamer (Na) 15	E/ 9% VA 22	PVDC 8	E/ 9% VA 14
Comp. 3	E/ 8% B 15	E/ 9% VA 22	PVDC 8	E/ 9% VA 14
Comp. 4	E/ 10.5% O 15	E/ 9% VA 22	PVDC 8	E/ 9% VA 14
1	E/ 15% B 15	E/ 9% VA 22	PVDC 8	E/ 9% VA 14
2	E/ 13% O 15	E/ 9% VA 22	PVDC 8	E/ 9% VA 14
3	E/ 19% O 15	E/ 9% VA 22	PVDC 8	E/ 9% VA 14

Table II

Example	Comparison 1	Comparison 2	Comparison 3	Comparison 4	Example 1	Example 2	Example 3
	VPHB	Shrink %	VPHB	Shrink %	VPHB	Shrink %	VPHB
Temperatures	mm	$\frac{L+T}{2}$	mm	$\frac{L+T}{2}$	mm	$\frac{L+T}{2}$	mm
	H <sub>2</sub> O	2	H <sub>2</sub> O	2	H <sub>2</sub> O	2	H <sub>2</sub> O
60°C		4		2		2	
70°C		11		7		7	
80°C	663	21	856	25			
85°C	652	30	782	45	1040	27	1074
90°C	520	41	644	24	940	16	990
95°C	318	57	540	28	783	33	802
100°C			420	49	647	53	621
			268	63	398	64	363
COLD SEAL							
STRENGTH	24.5	15.8	16.1	22.5	19.4		23.5
(kg/6 cm)	(103 no.						
	(breakage)						

When comparing the results it should be borne in mind that the shrink temperature should not exceed a value at which the hot-burst pressure drops below 650 mm/H<sub>2</sub>O. For some food products the maximum shrink temperature may be more limited but a higher hot-burst will then give additional safety. It is clear from the data in table II that comparison 1 gives good cold seal strength but the hot seal strength and the percent shrink leave something to be desired. Further, this material results in poor seal strength through

contamination like grease or blood. Comparison 2 shows improved shrink characteristics but the cold seal strength is considerably lower and this material cannot be sealed reliably through blood contamination.

Examples 1, 2 and 3 show that excellent shrink characteristics and a very good seal strength both at room temperature and at elevated temperatures are being obtained. It has further been found that the seal strength is not significantly affected by contamination like grease or blood. Comparisons 3 and 4 show that a very significant decrease both in seal strength and percent shrink occur when the comonomer content in the ethylene  $\alpha$ -olefin copolymer drops below a certain level, i.e. the minimum comonomer content is an essential feature if the combination of desired properties is to be achieved.

#### 10 COMPARATIVE EXAMPLES 5 AND 6, EXAMPLES 4 TO 10

Multi-layer packaging films of the composition summarized in the following table III were produced by conventional techniques, i.e. by coextruding a tubular film of layers A to F and subsequent stretching and orientation, e.g. in a blown-up bubble, so as to obtain a heat shrinkable film. No irradiation was employed in this case. The test results obtained are tabulated in the following table IV.

20

25

30

35

40

45

50

55



TABLE III

Example No.	A	B	C	D	E	F
	sealing layer $\mu\text{m}$	core layer $\mu\text{m}$	adhesion promoter $\mu\text{m}$	barrier layer $\mu\text{m}$	adhesion promoter $\mu\text{m}$	outer layer $\mu\text{m}$
Comp.5	ionomer (Na) 25	E/18% VA 9 + E/14% VA 43	acid modif. EVA 6	PVDC 8	acid modif. EVA 6	PA 23
Comp.6	E/8% B 25	E/18% VA 9 + E/14% VA 43	acid modif. EVA 6	PVDC 8	acid modif. EVA 6	PA 23
4	E/15% B 25	E/18% VA 9 + E/14% VA 43	acid modif. EVA 6	PVDC 8	acid modif. EVA 6	PA 23
5	E/13% D 25	E/18% VA 9 + E/14% VA 43	acid modif. EVA 6	PVDC 8	acid modif. EVA 6	PA 23
6	E/19% D 25	E/18% VA 9 + E/14% VA 43	acid modif. EVA 6	PVDC 8	acid modif. EVA 6	PA 23
7	75% E/13% O 25% + EVA	E/18% VA 9+ E/14% VA 43	acid modif. EVA 6	PVDC 8	acid modif. EVA 6	PA 23
8	90% E/13% O 10% acid modif. EVA	E/18% VA 9+ E/14% VA 43	acid modif. EVA 6	PVDC 8	acid modif. EVA 6	PA 23
9	50% E/13% O 50% E/4% VA	E/18% VA 9+ E/14% VA 43	acid modif. EVA 6	PVDC 8	acid modif. EVA 6	PA 23
10	50% E/15% B 50% P/4.5% E	E/18% VA 9+ E/14% VA 43	acid modif. EVA 6	PVDC 8	acid modif. EVA 6	PA 23

TABLE IV

Example	Comparison 5	Comparison 6	Example 4	Example 5	Example 6	Example 7	Example 8	Example 9	Example 10
Temperatures	mm	mm	mm	mm	mm	mm	mm	mm	mm
	$\frac{L+T}{2}$	$\frac{L+T}{2}$	$\frac{L+T}{2}$	$\frac{L+T}{2}$	$\frac{L+T}{2}$	$\frac{L+T}{2}$	$\frac{L+T}{2}$	$\frac{L+T}{2}$	$\frac{L+T}{2}$
	H <sub>2</sub> O	H <sub>2</sub> O	H <sub>2</sub> O	H <sub>2</sub> O	H <sub>2</sub> O	H <sub>2</sub> O	H <sub>2</sub> O	H <sub>2</sub> O	H <sub>2</sub> O
60°C	15	4.5	13.5	5	9	5	6	10	4
70°C	25	9.5	21.5	11	19.5	12	13	16	10
80°C	993	37	1084	1043	1007	1020	980	940	1150
85°C	877			892	753	850	780	720	810
90°C	617	43	835	710	560	700	670	610	700
95°C	381			534	431	525	510	470	560
100 °C	319	46	546	436	338	410	430	330	490
COLD SEAL STRENGTH (kg/6 cm)	17.6	25.6	32.7	29.6	28	32.0	34	32	25
			(70% no breakages)						

The results are essentially similar to those obtained with the irradiated material. Only the films of the present invention combine excellent shrink characteristics with outstanding cold and hot seal strength. In addition thereto they may be sealed without impairing the seal strength through contamination like grease or blood which are always encountered in the packaging of meat products. Further, the non-irradiated structures show the same effect, namely a strong dependency of the shrink and seal characteristics on the

comonomer content of the ethylene/  $\alpha$  -olefin copolymer.

#### Claims

- 5 1. A thermoplastic multi-layer packaging film having superior heat shrink and cold seal properties comprising at least an outer polymer layer, an inner heat sealing layer and optionally an oxygen barrier layer between said inner and said outer layer, characterized in that the heat sealing layer comprises a linear copolymer of ethylene and x to y% by weight, based on the copolymer, of an  $\alpha$  -olefin with 4 to 8 carbon atoms per molecule, wherein  $x = 0.5n_C + 8$  and  $y = 1.25n_C + 15$  with  $n_C$  being the number  
10 of carbon atoms in the  $\alpha$  -olefin, said copolymer having a density of 0.915 g/cm<sup>3</sup> or less.
2. The film of claim 1, characterized in that the heat sealing layer comprises a copolymer of ethylene and 12 to 20% by weight, based on the copolymer, of an  $\alpha$  -olefin with 4 to 8 carbon atoms.
- 15 3. The film of claim 1, characterized in that the heat sealing layer comprises a copolymer of ethylene and 10 to 20% by weight, based on the copolymer, of butene(1), said copolymer having a density of less than 0.915 g/cm<sup>3</sup>.
4. The film of claim 1, characterized in that the heat sealing layer comprises a copolymer of ethylene and  
20 12 to 25% by weight, based on the copolymer, of octene(1), said copolymer having a density of 0.915 g/cm<sup>3</sup> or less.
5. The film of anyone of claims 1 to 5, characterized in that the heat sealing layer comprises further up to 50% by weight, based on the layer composition, of a polymer which is compatible with said ethylene/  $\alpha$  -olefin copolymer and is selected from the group comprising linear low density polyethylene (LLDPE),  
25 linear high density polyethylene (LHDPE), low density polyethylene (LDPE), ethylene/vinyl acetate (EVA), acid modified EVA, polypropylene, ethylene/propylene copolymers, ionomers and ethylene/alkylacrylate copolymers having 1 to 8 C atoms in the respective alkyl radical.
- 30 6. The film of claim 5, wherein said polymer compatible with said ethylene/  $\alpha$  -olefin copolymer is an ethylene/alkylacrylate copolymer selected from ethylene-methylacrylate, ethylene-ethylacrylate and ethylene-butylacrylate.
7. The film of anyone of claims 1 to 6, characterized in that the outer polymer layer is of a polymer  
35 selected from the group comprising a copolymer of ethylene and 10 to 25% by weight, based on the copolymer, of an  $\alpha$  -olefin with 4 to 8 carbon atoms, said copolymer having a density of less than 920 kg/m<sup>3</sup>, EVA, polyamide, and ionomeric resins.
8. The film of anyone of claims 1 to 7, characterized in that the oxygen barrier layer comprises a polymer  
40 selected from the group comprising polyvinylidene chloride (PVDC) and hydrolized ethylene/vinyl acetate copolymers (EVOH).
9. The film of anyone of claims 1 to 8, characterized in that an adhesive layer and/or an adhesion promoting layer is interposed between said other layers.
- 45 10. The film of anyone of claims 1 to 9, characterized in that at least the heat sealing layer has been cross-linked by irradiation.
11. The film of claim 10, characterized in that the oxygen barrier layer comprises EVOH and that the entire  
50 multi-layer film has been irradiated.
12. A side-sealed bag formed from the film of anyone of claims 1 to 11, said film being folded so that the fold forms the bottom of the bag and side-seals close both sides of the bag.
- 55 13. A bag formed from a tubular film of anyone of claims 1 to 11 wherein the bottom of the bag is formed by a transverse seal across the flattened tube and the mouth is formed by severing the tube at a pre-selected distance from said transverse seal.

## Revendications

1. Feuille thermoplastique multicouche d'emballage, ayant des propriétés supérieures de rétrécissement à la chaleur et de scellement à froid comprenant au moins une couche externe d'un polymère, une  
5 couche interne de scellement à la chaleur et facultativement, une couche formant barrière d'oxygène entre ladite couche interne et ladite couche externe caractérisée en ce que la couche de scellement à la chaleur comprend un copolymère d'éthylène et  $x$  à  $y\%$  en poids, en se basant sur le copolymère, d'une  $\alpha$ -oléfine avec 4 à 8 atomes de carbone par molécule, où  $x = 0,5n_c + 8$  et  $y = 1,25n_c + 15$ ,  $n_c$  étant le nombre d'atomes de carbone dans l' $\alpha$ -oléfine, ledit copolymère ayant une densité de 0,915  
10 g/cm<sup>3</sup> ou moins.
2. Feuille de la revendication 1, caractérisée en ce que la couche de scellement à la chaleur comprend un copolymère d'éthylène et 12 à 20% en poids, en se basant sur le copolymère, d'une  $\alpha$ -oléfine ayant 4 à 8 atomes de carbone.
3. Feuille de la revendication 1, caractérisée en ce que la couche de scellement à la chaleur comprend un copolymère d'éthylène ayant 10 à 20% en poids, en se basant sur le copolymère, de butène(1), ledit  
15 copolymère ayant une densité de moins de 0,915 g/cm<sup>3</sup>.
4. Feuille de la revendication 1, caractérisée en ce que la couche de scellement à la chaleur comprend un copolymère d'éthylène et 12 à 25% en poids, en se basant sur le copolymère, d'octène(1), ledit  
20 copolymère ayant une densité de 0,915 g/cm<sup>3</sup> ou moins.
5. Feuille selon l'une quelconque des revendications 1 à 5, caractérisée en ce que la couche de scellement à la chaleur comprend de plus jusqu'à 50% en poids, en se basant sur la composition de la  
25 couche, d'un polymère qui est compatible avec ledit copolymère d'éthylène/ $\alpha$ -oléfine et est choisi dans le groupe comprenant du polyéthylène linéaire de faible densité (LLDPE) du polyéthylène linéaire de forte densité (LHDPE), du polyéthylène de faible densité (LDPE), de l'éthylène/acétate de vinyle (EVA), EVA modifié à l'acide, du polypropylène, des copolymères d'éthylène/propylène, des ionomères et des  
30 copolymères d'éthylène/acrylate d'alkyle ayant 1 à 8 atomes de C dans le radical alkyle respectif.
6. Feuille de la revendication 5, où ledit polymère compatible avec ledit copolymère d'éthylène/ $\alpha$ -oléfine est un copolymère d'éthylène/acrylate d'alkyle choisi parmi l'éthylène-acrylate de méthyle, l'éthylène-  
35 acrylate d'éthyle et l'éthylène-acrylate de butyle.
7. Feuille selon l'une quelconque des revendications 1 à 6, caractérisée en ce que la couche externe du polymère est d'un polymère choisi dans le groupe comprenant un copolymère d'éthylène et 10 à 25%  
40 en poids, en se basant sur le copolymère, d'une  $\alpha$ -oléfine avec 4 à 8 atomes de carbone, ledit copolymère ayant une densité de 0,915 g/cm<sup>3</sup> ou moins, EVA, polyamide, et résines ionomères.
8. Feuille selon l'une quelconque des revendications 1 à 7, caractérisée en ce que la couche formant barrière contre l'oxygène comprend un polymère choisi dans le groupe comprenant du chlorure de  
polyvinylidène (PVDC) et des copolymères hydrolysés d'éthylène/acétate de vinyle (EVOH).
9. Feuille selon l'une quelconque des revendications 1 à 8, caractérisée en ce qu'une couche adhésive  
45 et/ou une couche favorisant l'adhérence est interposée entre lesdites autres couches.
10. Feuille selon l'une quelconque des revendications 1 à 9, caractérisée en ce qu'au moins la couche de scellement à la chaleur a été réticulée par irradiation.
11. Feuille selon la revendication 10, caractérisée en ce que la couche formant barrière contre l'oxygène  
50 comprend EVOH et en ce que toute la feuille multicouche a été irradiée.
12. Sac scellé latéralement, formé de la feuille selon l'une quelconque des revendications 1 à 11, ladite  
55 feuille étant pliée de manière que le pli forme le fond du sac et que les joints latéraux ferment les deux côtés du sac.
13. Sac formé d'une feuille tubulaire selon l'une quelconque des revendications 1 à 11, où le fond du sac

est formé d'un joint transversal à travers le tube aplati et l'embouchure est formée en rompant le tube à une distance présélectionnée du joint transversal.

# Patentansprüche

- 5 1. Thermoplastische Mehrschicht-Verpackungsfolie mit verbesserten Heißschrumpf- und Kaltsiegeleigenschaften, welche mindestens eine äußere Polymerschicht, eine innere Heißsiegelschicht und gegebenenfalls eine Sauerstoffsperrschicht zwischen der inneren und äußeren Schicht umfaßt, **dadurch gekennzeichnet**, daß die Heißsiegelschicht ein Copolymer aus Ethylen und x bis y Gew.%, bezogen auf das  
10 Copolymer, eines  $\alpha$ -Olefins mit 4 bis 8 Kohlenstoffatomen je Molekül enthält, wobei  $x = 0,5 n_c + 8$  und  $y = 1,25 n_c + 15$  ist und  $n_c$  die Zahl der Kohlenstoffatome in dem  $\alpha$ -Olefin ist, und das Copolymer eine Dichte von 0,915 g/cm<sup>3</sup> oder weniger aufweist.
- 15 2. Folie nach Anspruch 1, **dadurch gekennzeichnet**, daß die Heißsiegelschicht ein Copolymer aus Ethylen und 12 bis 20 Gew.%, bezogen auf das Copolymer, eines  $\alpha$ -Olefins mit 4 bis 8 Kohlenstoffatomen umfaßt.
3. Folie nach Anspruch 1, **dadurch gekennzeichnet**, daß die Heißsiegelschicht ein Copolymer aus Ethylen und 10 bis 20 Gew.%, bezogen auf das Copolymer, Buten(1) umfaßt, wobei das Copolymer  
20 eine Dichte von weniger als 0,915 g/cm<sup>3</sup> aufweist.
4. Folie nach Anspruch 1, **dadurch gekennzeichnet**, daß die Heißsiegelschicht ein Copolymer aus Ethylen und 12 bis 25 Gew.%, bezogen auf das Copolymer, Octen(1) umfaßt, wobei das Copolymer eine Dichte von 0,915 g/cm<sup>3</sup> oder weniger aufweist.
- 25 5. Folie nach einem der Ansprüche 1 bis 5, **dadurch gekennzeichnet**, daß die Heißsiegelschicht weiterhin bis zu 50 Gew.%, bezogen auf die Schichtzusammensetzung, eines Polymeren umfaßt, das mit dem Ethylen/ $\alpha$ -Olefin-Copolymer verträglich ist und aus der Gruppe ausgewählt ist, die lineares Polyethylen niederer Dichte (LLDPE), lineares Polyethylen hoher Dichte (LHDPE), Polyethylen niederer  
30 Dichte (LDPE), Ethylen/Vinylacetat (EVA), säuremodifiziertes EVA, Polypropylen, Ethylen/Propylen-Copolymere, Ionomere und Ethylen/Alkylacrylat-Copolymere mit 1 bis 8 Kohlenstoffatomen in den jeweiligen Alkylresten umfaßt.
- 35 6. Folie nach Anspruch 5, bei der das mit dem Ethylen/ $\alpha$ -Olefin-Copolymerverträgliche Polymer ein Ethylen/Alkylacrylat-Copolymer ist, das ausgewählt ist aus Ethylen-Methylacrylat, Ethylen-Ethylacrylat und Ethylen-Butylacrylat.
7. Folie nach einem der Ansprüche 1 bis 6, **dadurch gekennzeichnet**, daß die äußere Polymerschicht aus einem Polymer besteht, das aus der Gruppe ausgewählt ist, die ein Copolymer aus Ethylen und 10  
40 bis 25 Gew.%, bezogen auf das Copolymer, eines  $\alpha$ -Olefins mit 4 bis 8 Kohlenstoffatomen, wobei das Copolymer eine Dichte von 0,915 g/cm<sup>3</sup> oder weniger aufweist, EVA, Polyamid und Ionomerharze umfaßt.
8. Folie nach einem der Ansprüche 1 bis 7, **dadurch gekennzeichnet**, daß die Sauerstoffsperrschicht ein Polymer umfaßt, das aus der Gruppe ausgewählt ist, die Polyvinylidenchlorid (PVDC) und hydrolysierte Ethylen/Vinylacetat-Copolymere (EVOH) umfaßt.
- 45 9. Folie nach einem der Ansprüche 1 bis 8, **dadurch gekennzeichnet**, daß eine Klebstoffschicht und/oder eine die Haftung verbessernde Schicht zwischen den anderen Schichten angeordnet ist.
- 50 10. Folie nach einem der Ansprüche 1 bis 9, **dadurch gekennzeichnet**, daß mindestens die Heißsiegelschicht durch Strahlung vernetzt worden ist.
11. Folie nach Anspruch 10, **dadurch gekennzeichnet**, daß die Sauerstoffsperrschicht EVOH umfaßt und  
55 daß die gesamte Mehrschichtfolie bestrahlt worden ist.
12. Ein an den Seiten verschweißter Beutel aus der Folie gemäß einem der Ansprüche 1 bis 11, bei dem die Folie so gefaltet ist, daß die Faltung den Boden des Beutels bildet und die seitlichen Siegelnähte

beide Seiten des Beutels verschließen.

- 5 13. Beutel aus einer schlauchförmigen Folie, gemäß einem der Ansprüche 1 bis 11, bei dem der Boden des Beutels von einer Versiegelung quer über den flachgelegten Folienschlauch gebildet wird und die Beutelöffnung dadurch gebildet wird, daß der Schlauch in einem vorgewählten Abstand von der Querversiegelung abgeschnitten ist.

10

15

20

25

30

35

40

45

50

55